



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : D21C 9/00, D21H 21/14, 17/07		A1	(11) International Publication Number: WO 00/24963
			(43) International Publication Date: 4 May 2000 (04.05.00)
(21) International Application Number: PCT/EP99/07594		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 11 October 1999 (11.10.99)			
(30) Priority Data: 09/177,016 22 October 1998 (22.10.98) US 09/234,253 20 January 1999 (20.01.99) US 60/116,688 20 January 1999 (20.01.99) US			
(71) Applicant: CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).			
(72) Inventors: SELTZER, Raymond; 11 Angus Lane, New City, NY 10956 (US). DEVORE, David; 10 Forest Ridge Road, Nyack, NY 10960 (US). CUNKLE, Glen, Thomas; 65 Malibu Road, Stamford, CT 06903 (US). HEITNER, Cyril; 4466 Glendale, Pierrefonds, Quebec H9H 2L2 (CA). SCHMIDT, John, Alois; 445 Cr. Boyer, L'ile Bizard, Quebec H9C 1L2 (CA). MCGARRY, Peter, Francis; 337 Rue Sainte Marie, L'ile Bizard, Quebec H9C 1L2 (CA). WOLF, Jean-Pierre; Chilmetweg 6, CH-4464 Maisprach (CH). NELSON, Randall, Bruce; 1717 16th Avenue, No. 23, Seattle, WA 98122 (US).		Published <i>With international search report.</i>	
(54) Title: INHIBITION OF PULP AND PAPER YELLOWING USING HYDROXYLAMINES AND OTHER COADDITIVES			
(57) Abstract <p>Pulps or papers, especially chemimechanical or thermomechanical pulps or papers, which still contain lignin, have enhanced resistance to yellowing when they contain an effective stabilizing amount of a N,N-dialkylhydroxylamine, an ester, amide or thio substituted N,N-dialkylhydroxylamine or N,N-dibenzylhydroxylamine or an ammonium salt thereof. This performance is often further enhanced by the presence of one or more coadditives selected from the group consisting of the UV absorbers, the polymeric inhibitors, the nitrones, the fluorescent whitening agents and metal chelating agents. Combinations of hydroxylamines or their salts, benzotriazole or benzophenone UV absorbers and a metal chelating agent are particularly effective. N,N-Diethylhydroxylamine and N,N-dibenzylhydroxylamine and their acid salts are surprisingly effective for this purpose.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INHIBITION OF PULP AND PAPER YELLOWING
USING HYDROXYLAMINES AND OTHER COADDITIVES

The instant invention pertains to a method for preventing the loss of brightness and for enhancing resistance to yellowing in pulp or paper, particularly pulp or paper which still contains lignin, by the addition of N,N-dialkylhydroxylamines, an ester, amide or thio substituted N,N-dialkylhydroxylamine or N,N-dibenzylhydroxylamine, or their salts and other coadditives.

Background of the Invention

High-yield and ultra-high yield wood pulps undergo rapid light-induced discoloration, particularly when they are exposed to near ultraviolet light (wave lengths 300-400 nm) in indoor fluorescent light and daylight. This characteristic restricts their use to short-life, low-value paper products. High-yield and ultra-high yield wood pulps can be bleached to a high level of whiteness. If this whiteness could be stabilized against discoloration, these bleached high-yield pulps could displace significant amounts of more expensive fully-bleached, low-yield chemical pulps.

This discoloration is ascribed to the substantial lignin content of high-yield pulps totally about 20-30% by mass. Phenoxy radicals are the key intermediates in the reaction mechanism. Several light-induced reactions have been proposed to account for their formation such as cleavage of the aryl ether bond of phenacyl aryl ether groups, or breakdown of ketyl radicals formed from saturated aryl-glycerol β -aryl ether structures in lignin. The phenoxy radicals are oxidized by other oxygen-centered radicals (alkoxy and perhydroxy) to form yellow chromophores.

I. E. Arzkin et al., Khymiya drevesiny (Chemistry of Wood), 1982, No. 2, 114 and A. D. Sergeev et al., *ibid*, 1984, No. 5, 20 disclosed that the use of iminoxyl radicals such as TEMPO (1-oxyl-2,2,6,6-tetramethylpiperidine) is useful in the delignification of wood using the one-stage oxygen-soda (alkaline) process, but made no mention or suggestion of any activity provided by TEMPO on preventing light-induced discoloration of paper or pulp made from such treated wood.

V. I. Khodyrev et al., Vysokomol soyed, A29, No. 3, 616 (1987) [Polymer Sci. U.S.S.R., 29, No. 3, 688 (1987)] show that the photoinitiated oxidation by oxygen causes weathering of cellulosic textile materials such as flax or cotton, and that the light stability of the cellulose could be improved by photostabilizers such as the UV absorbers, benzophenols and 1-oxy-2,2,6,6-tetramethyl-4-hydroxypiperidine. The UV absorbers offer no protection, and are actually detrimental. The authors noted that the stable nitroxyl radical interacts with alkyl radicals in the cellulose to afford its salubrious stabilizing activity. There is no suggestion by the authors that this stabilizing activity could be applied successfully in wood pulp and/or paper made therefrom.

M-K. Syler et al., J. Assn. Paper Pulp Tech, 29, 135 (1990) show that selected metal salts such as magnesium sulfate and lower alkanolic acids inhibit color reversion in bleached pulp.

P. Fornier de Violet et al., Cellulose Chem. Tech., 24, 225 (1990) show that the use of UV absorbers and hydrogen donor agents such as thiols, ascorbic acid, etc. help prevent the photoinduced discoloration of hydrogen peroxide bleached wood pulp, but that chain breakers such as hindered phenols and hindered amines (having >N-H or >N-CH₂- moieties) had no or even a detrimental effect on preventing photoinduced discoloration.

R. Agnemo et al., 6th International Symposium on Wood and Pulping Chemistry, Appita, 1991, confirmed that free hydroxyl radicals plus lignin lead to undesirable photoyellowing in pulp and paper.

S. Omori et al., J. Assn. Paper Pulp Tech, 48, 1388 (1993) describes the effect of antioxidants and UV absorbers on light reversion and concludes that the combination of an antioxidant and UV absorber prevents color reversion and has a synergistic effect in that activity.

M. Paulsson et al., 8th International Symposium Wood and Pulping Chemistry, Helsinki, 1995, show that efficient photostabilization of unbleached paper or hydrogen peroxide bleached TMP pulp can be achieved by acetylation.

There have been a number of different approaches proposed to inhibiting the yellowing of mechanical pulps. These include: radical scavengers and antioxidants; UV screens; elimination of chromophores after their formation; chemical modification of lignin by alkylation or acetylation; polymeric inhibitors; and two types of coadditives used in combination. Z-H. Wu et al., *Holzforschung*, 48, (1994), 400 discuss the use of radical scavengers like phenyl-N-tert-butyl-nitron to reduce the formation of chromophores during mechanical pulping and give a more light-stable pulp.

C. Heitner, *Chemistry of Brightness Reversion and Its Control*, Chapter 5, TAPPI, Atlanta, 1996, pp 183-211, summarizes the state of the art in the thermal and light-induced yellowing of lignin-containing pulps such as thermomechanical (TMP) and chemithermomechanical (CTMP) pulps, showing the seriousness of these undesirable effects discusses generally the then current prior art methods used to attack this problem. These include bleaching, the use of phosphites, UV absorbers, polyalkylene glycols and free radical scavengers such as ascorbic acid, thiols, thioethers, dienes and aliphatic aldehydes and chelating agents such as ethylenediaminetetraacetic acid (EDTA). The author concluded that, although much progress had been made, much still remains to be done before a successful and practical solution to this loss of brightness and undesirable yellowing of lignin-containing pulp and/or paper is found.

WO 99/05108 describes a potential solution where the use of selected hindered amine nitroxides, hindered amine hydroxylamines or their salts in combination with selected UV absorbers and metal chelating agents is seen to prevent loss of brightness and to enhance resistance to yellowing in pulp or paper still containing lignin.

Canadian Patent Application No. 2,164,394 and WO 97/36041 teach a multi-component system for modifying, degrading or bleaching lignin-containing materials. This system includes an oxidation catalyst as an essential component. The catalysts are selected enzymes such as oxidoreductases of classes 1.1.1 to 1.97. The system also includes a number of mediators which inter alia include lower N,N-dialkylhydroxylamines and N,N-dibenzylhydroxylamine.

The instant invention describes another approach to this important problem where the use of N,N-dialkylhydroxylamine, an ester, amide or thio substituted N,N-dialkylhydroxyl-

amine or N,N-dibenzylhydroxylamine or their salts in combination with selected coadditives also prevents the loss of brightness and enhances resistance to yellowing in pulp or paper, especially pulp or paper still containing lignin. The ester, amide or thio substituted N,N-dialkylhydroxylamines are described in United States Patent Nos. 4,612,393; 4,720,517 and 5,019,285.

Detailed Description of the Invention

The addition of N,N-dialkylhydroxylamines, derivatives thereof or N,N-dibenzylhydroxylamine to pulp or paper either alone or in combinations with UV absorbers, metal chelating agents, fluorescent whitening agents and/or stabilizing polymers effectively achieves a distinctly improved light and thermal stability. Addition to chemimechanical or thermomechanical pulps or papers, which still contain major amounts of lignin, leads to a light and thermal stability which is similar to that found in papers made from (chemical) kraft pulps. Addition to a kraft pulp or paper, which may still contain traces of lignin, leads to a distinct improvement of the light and thermal stability.

The addition of N,N-dialkylhydroxylamines, derivatives thereof or N,N-dibenzylhydroxylamine to high-yield pulp or paper which still contain lignin either alone or in combinations with UV absorbers, metal chelating agents, fluorescent whitening agents and/or stabilizing polymers effectively achieves light and thermal stability which is similar to that found in papers made from kraft pulps.

Hydroxylamines are known to be efficient free radical traps and may limit the production of o-quinones; UV absorbers limit photochemistry in the underlying substrate to which they are applied, and ultimately reduce the production of free radicals. UV absorbers and hydroxylamines are each effective at stemming some of the free radical chemistry leading to paper yellowing when used singly. However, when they are used together, hydroxylamines and UV absorbers can act synergistically to effectively stop photochemical yellowing of lignin containing papers. The hydroxylamines show enhanced inhibiting activity when combined with a metal chelating agent such diethylenetriaminepentaacetic acid or citric acid, or polymeric inhibitors such as polyethylene glycol.

More particularly, the instant invention pertains to a composition having enhanced resistance to yellowing which comprises

(a) a pulp or paper, especially a pulp or paper which still contains lignin, and

(b) an effective stabilizing amount of an N,N-dialkylhydroxylamine, an ester, amide or thio substituted N,N-dialkylhydroxylamine or N,N-dibenzylhydroxylamine of formula I, II or III





where

R_1 and R_2 are independently alkyl of 1 to 18 carbon atoms, alkyl of 1 to 18 carbon atoms substituted by a hydroxyl group; or benzyl;

T_1 and T_2 are independently alkyl of 1 to 4 carbon atoms, phenyl, 3,5-di-tert-butyl-4-hydroxyphenyl, benzyl or $-CH_2COOH$;

E_1 and E_2 are independently $-OE_3$, $-NHE_3$ or $-NE_3E_4$ where E_3 and E_4 are independently hydrogen, alkyl of 1 to 4 carbon atoms or said alkyl substituted by one hydroxyl group; or

of an acid salt of formula IA, IIA or IIIA



where

X is an inorganic or organic anion, and

the total charge of cations h is equal to the total charge of anions j .

Preferably, X is phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride, bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid, hydroxyethylethylenediaminetriacetic acid, ethylenediaminetetraacetic acid or of diethylenetriaminepentaacetic acid, a diethylenediaminetetraacetic acid or of diethylenetriaminepentaacetic acid, an alkylsulfonate or an arylsulfonate.

Preferably the hydroxylamine is N,N-dimethylhydroxylamine, N,N-diethylhydroxylamine, N,N-bis(2-hydroxypropyl)hydroxylamine, N,N-bis(3-hydroxypropyl)hydroxylamine, N,N-dioctadecylhydroxylamine, the N,N-dialkylhydroxylamine product made by the direct oxidation of N,N-di(hydrogenated tallow)amine, N,N-dibenzylhydroxylamine, N,N-bis(2-carboxyethyl)hydroxylamine or N,N-bis(benzylthiomethyl)hydroxylamine.

Most preferably, the hydroxylamine is N,N-diethylhydroxylamine, N,N-bis(2-hydroxypropyl)hydroxylamine, N,N-bis(3-hydroxypropyl)hydroxylamine or N,N-dibenzylhydroxylamine; most especially N,N-diethylhydroxylamine or its citric acid salt.

It is shown that the salts of these hydroxylamines are also beneficial in producing the increase in brightness and the resistance to yellowing in pulp or paper, especially when still containing lignin.

The effective stabilizing amounts of the hydroxylamine is 0.001 to 5% by weight based on the pulp or paper. Preferably, the effective stabilizing amount is 0.005 to 4% by weight; preferably 0.01 to 4% by weight.

When a coadditive stabilizer is also present, the effective stabilizing amount of the coadditives is also 0.001 to 5% by weight based on the pulp or paper; preferably 0.005 to 3% by weight; most preferably 0.01 to 2% by weight.

The instant compounds may additionally include an effective stabilizing amount of at least one stabilizer selected from the group consisting of the UV absorbers, the polymeric

inhibitors, the sulfur containing inhibitors, the phosphorus containing compounds, the nitrones, the benzofuran-2-ones, fluorescent whitening agents, hindered amine hydroxylamines and salts thereof, hindered amine nitroxides and salts thereof, hindered amines and salts thereof and metal chelating agents.

The compositions which also include a UV absorber are especially preferred. The UV absorber is selected from group consisting of the benzotriazoles, the s-triazines, the benzophenones, the α -cyanoacrylates, the oxanilides, the benzoxazinones, the benzoates and the α -alkyl cinnamates.

Preferably, the UV absorber is a benzotriazole, an s-triazine or a benzophenone, most especially a benzotriazole UV absorber or benzophenone UV absorber.

Typical and useful UV absorbers are, for example,

- 5-chloro-2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-3,5-di- α -cumylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-3- α -cumyl-5-tert-octylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-5-tert-octylphenyl)-2H-benzotriazole;
- 2-(2-hydroxy-3-tert-butyl-5-methylphenyl)-2H-benzotriazole-5-sulfonic acid, sodium salt;
- 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamic acid;
- 12-hydroxy-3,6,9-trioxadodecyl 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamate;
- octyl 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamate;
- 4,6-bis(2,4-dimethylphenyl)-2-(4-(3-dodecyloxy*-2-hydroxypropoxy)-2-hydroxyphenyl)-s-triazine (*is mixture of C₁₂₋₁₄oxy isomers);
- 4,6-bis(2,4-dimethylphenyl)-2-(4-octyloxy-2-hydroxyphenyl)-s-triazine;
- 4,6-diphenyl-2-(4-{2-(1-ethylpentyl-carbonyloxy)ethoxy}-2-hydroxyphenyl)-s-triazine;
- 2,4-dihydroxybenzophenone;
- 2,2',4,4'-tetrahydroxy-5,5'-disulfobenzophenone, disodium salt;
- 2-hydroxy-4-octyloxybenzophenone;

2-hydroxy-4-dodecyloxybenzophenone;
2,4-dihydroxybenzophenone-5-sulfonic acid and salts thereof;
2-hydroxy-4-methoxybenzophenone-5-sulfonic acid and salts thereof;
2,2'-dihydroxy-4,4'-dimethoxybenzophenone-5,5'-disodium sulfonate; and
3-(2H-benzotriazol-2-yl)-4-hydroxy-5-sec-butylbenzenesulfonic acid, sodium salt
(CIBAFast W).

Other preferred compositions are those which additionally contain a polymeric inhibitor; preferably poly(ethylene glycol), poly(propylene glycol), poly(butylene glycol) or poly(vinyl pyrrolidone).

Still other preferred compositions are those wherein the additional stabilizer is a sulfur containing inhibitor; preferably polyethylene glycol dithiolacetate, polypropylene glycol dithiolacetate, polybutylene glycol dithioacetate, 1-thioglycerol, 2-mercaptoethyl ether, 2,2'-thiodiethanol, 2,2'-dithiodiethanol, 2,2'-oxydiethanethiol, ethylene glycol bithioglycolate, 3-mercapto-1,2-propanediol, 2-(2-methoxyethoxy)-ethanethiol, glycol dimercaptoacetate, 3,3'-dithiopropionic acid, polyethylene glycol dithiol, polypropylene glycol dithiol, polybutylene glycol dithiol or ethylene glycol bis(mercaptoacetate).

Other preferred compositions are those wherein the additional stabilizer is a phosphorus containing compound; preferably tris(2,4-di-tert-butylphenyl) phosphite, 2,2',2''-nitriolo[triethyl-tris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl) phosphite], bis(2,4-di-tert-butyl-6-methylphenyl) ethyl phosphite, sodium hydroxymethyl phosphinate, tetrakis(2,4-di-butylphenyl) 4,4'-biphenylenediphosphonite, tris(nonylphenyl) phosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, 2,2'-ethylidenebis(2,4-di-tert-butylphenyl) fluorophosphite or 2-butyl-2-ethylpropan-1,3-diyl 2,4,6-tri-tert-butylphenyl phosphite.

Still other preferred compositions are those wherein the additional stabilizer is a benzofuran-2-one; preferably 5,7-di-tert-butyl-3-(3,4-dimethylphenyl)-2H-benzofuran-2-one.

Still other preferred composition are those wherein the additional stabilizer is a metal chelating agent; preferably citric acid, keto acids, gluconates, heptagluconates, phosphates, phosphonates and aminocarboxylic acid chelates, such as ethylenediaminetetraacetic acid (EDTA), diethylenetriaminepentaacetic acid (DTPA), hydroxyethylethylenediaminetriacetic

acid (HEDTA), nitrilotriacetic acid (NTA) and diethylenetriaminepentamethylenephosphonic acid (DTPMPA).

Some preferred compositions contain a mixture of additional stabilizers such as a mixture of a UV absorber and polymeric inhibitor; or a mixture of a UV absorber and a sulfur containing compound; or a mixture of a UV absorber and a phosphorus containing compound; or a mixture of a UV absorber and a metal chelating agent; or a mixture of a polymeric inhibitor and a sulfur containing compound; or a mixture of a polymeric inhibitor and a phosphorus containing compound; or a mixture of a sulfur containing compound and a phosphorus containing compound; or a mixture of a UV absorber, a polymeric inhibitor and a sulfur containing compound; or a mixture of a UV absorber, a polymeric inhibitor and a phosphorus containing compound; or a mixture of a UV absorber, a polymeric inhibitor, a sulfur containing compound and a phosphorus containing compound; or a mixture of a UV absorber, a polymeric inhibitor and a metal chelating agent.

Some preferred compositions are those wherein the additional stabilizer is a mixture of a hindered amine hydroxylamine or hindered amine hydroxylamine salt with at least one other stabilizer selected from the group consisting of the UV absorbers, the polymeric inhibitors, the sulfur containing inhibitors, the phosphorus containing compounds, fluorescent whitening agents (optical brighteners), metal chelating agents and hindered amine nitroxides and salts thereof.

Also preferred are compositions wherein the additional stabilizer is a mixture of a UV absorber, a polymeric inhibitor and a sulfur containing compound; or a UV absorber, a polymeric inhibitor and a phosphorus containing compound; or a UV absorber, a polymeric inhibitor and a metal chelating agent; or a UV absorber, a polymeric inhibitor, a sulfur containing compound and a phosphorus containing compound; or a UV absorber and a hindered amine nitroxide; or a UV absorber and a hindered amine hydroxylamine; or a UV absorber and a hindered amine hydroxylamine salt.

(Sterically) hindered amine nitroxides, hydroxylamines or hydroxylamine salts are mainly the compounds disclosed in WO 99/05108 (see formulae A to EE and A* to EE* therein, especially compounds (a) to (mm)).

Some preferred composition are those wherein the additional stabilizer is a mixture of a hindered amine hydroxylamine with at least one optical brightener such as 2,2'-[(1,1'-diphenyl)-4,4'-diyl-1,2-ethenediyl]bis-benzenesulfonic, disodium salt (or bis[4,4'-(2-stilbenesulfonic acid)], disodium salt) which is TINOPAL SK (Ciba Specialty Chemicals).

Preferably the compositions are those wherein the compound of formula I, II, III, IA, IIA or IIIA is of low molecular weight or contains hydrophilic moieties or is both of low molecular weight and contains hydrophilic moieties.

The instant invention also pertains to a process for preventing the loss of brightness and for enhancing resistance to yellowing of a pulp or paper, particularly a chemimechanical or thermomechanical pulp or paper which still contain lignin, or a chemical pulp or paper or kraft pulp or paper which still contains traces of lignin, which comprises

treating said pulp or paper with an effective stabilizing amount of a compound of formula I, II or III, or formula IA, IIA or IIIA as described above.

The instant inhibitor additive system can be added to pulp or paper at a number of places during the manufacturing or processing operations. These include

- a. on a pulp slurry in the latency chest;
- b. on a pulp slurry in or after the bleaching stage in a storage, blending or transfer chest;
- c. on pulp during or after bleaching, washing and dewatering followed by cylinder or flash drying;
- d. before or after the cleaners;
- e. before or after the fan pump to the paper machine headbox;
- f. to the paper machine white water;
- g. to the silo or save all;
- h. in the press section using a size press, coater or spray bar;
- i. in the drying section using a size press, coater or spray bar;
- j. on the calender using a wafer box;
- k. on paper in an off-machine coater or size press; and/or
- l. in the curl control unit.

Clearly, the precise location where the stabilizer additives should be added will depend on the specific equipment involved, the exact process conditions being used and the like. In some cases, the additives may be added at one or more locations for most effectiveness.

If the stabilizer or other coadditives are not themselves "water-soluble", they may be dispersed or emulsified by standard methods prior to application. Alternatively, the stabilizer and/or coadditives may be formulated into a paper sizing or paper coating formulation.

The following examples are for illustrative purposes only and are not to be construed to limit the instant invention in any manner whatsoever.

Handsheet Treatment

All additives are applied by syringe-injecting the appropriate weight % of additive combination in either an aqueous solution when the additive is water soluble, or a solution in 1:1 ethanol/dioxane, onto bleached thermomechanical pulp (BTMP) or chemical (kraft) pulp brightness squares (4 cm x 4cm). The clamped sheets are allowed to air dry for one day.

The brightness of the handsheets is recorded before and after treatment by light exposure under controled intensity conditions.

Accelerated testing is carried out by subjecting the treated sheets to accelerated light induced yellowing in a fan-cooled light box containing eight fluorescent lamps with a spectral maximum output at 5700 Å with a total output approximately 43 times greater than normal office fluorescent lamps. The lamps are about ten inches away from the handsheets being illuminated.

Ambient testing is carried out by placing the treated handsheets on a desk under normal cool-white fluorescent office lights at a nominal distance of six feet.

In both cases, ISO brightness is tracked as a function of photolysis time and converted to post color number (PC number) in the usual manner.

Post color (PC) number is defined as follows:

$$PC = [(k/s)_{\text{after}} - (k/s)_{\text{before}}] \times 100$$

$$k/s = (1 - R_{\text{inf}})^2 / 2 R_{\text{inf}}$$

where k and s are the absorption and scattering coefficients, respectively, and R_{inf} is the value of ISO brightness.

The relationship between R_{inf} and the chromophore concentration is non-linear, whereas, the PC number is roughly linearly related to the concentration of the chromophore in the sample.

Low PC numbers are desired as they indicate less yellowing.

When, using the ambient test conditions, untreated BTMP handsheets are compared to Kraft handsheets after 60 days, the BTMP handsheets have a PC number which is about 10 while the Kraft paper has a PC number which is about 0.39. The Kraft handsheets are clearly less yellow than untreated BTMP handsheets after exposure to ambient light.

The incident light flux for the accelerated yellowing experiments (Examples 1-10) is 43 times greater than normal office fluorescent lamps as measured by the A. W. Speery SLM-110 digital light power meter. The brightness of the handsheets is tracked and compared to that of untreated sheets exposed in the same manner. The treated sheets exhibit significant resistance to yellowing as is seen below.

Materials Used in the Examples

Compound A is N,N-diethylhydroxylamine.

Compound B is N,N-dibenzylhydroxylamine.

Compound C is N,N-dioctadecylhydroxylamine.

Compound D is the N,N-dialkylhydroxylamine product made by the direct oxidation of N,N-di(hydrogenated tallow)amine.

Compound E is tris(N,N-diethylhydroxylammonium) citrate.

PEO is poly(ethylene glycol) of molecular weight 300.

TINUVIN®328 (Ciba) is 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole.

TINOPAL® SK (Ciba) is 2,2'-[(1,1'-diphenyl)-4,4'-diyl-1,2-ethenediyl]bis-benzenesulfonic, disodium salt {or bis[4,4'-(2-stilbenesulfonic acid)], disodium salt}.

CIBAFast® W (Ciba) is 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-sec-butylbenzenesulfonic acid, sodium salt.

Compound F is N,N-bis(2-carboxyethyl)hydroxylamine.

Compound G is N,N-bis(benzylthiomethyl)hydroxylamine.

Example 1

Accelerated Yellowing with High Intensity Lamps, Bleached Thermomechanical Pulp (BTMP)

A BTMP sheet is treated with 1.0% by weight of N,N-diethylhydroxylamine (Compound A) and exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet as seen by inspection of the PC numbers given in the table below. Lower PC numbers indicate less color.

<u>Time</u> <u>hours</u>	<u>Compound A</u> <u>PC number</u>	<u>Control</u> <u>PC number</u>
0	0	0
23.6	2.28	5.14
29.4	2.86	6.07
48.7	5.00	9.01
97.8	10.40	15.75
120.3	12.95	18.54
144.0	15.77	21.48
172.2	19.10	24.95

Example 2

Accelerated Yellowing with High Intensity Lamps

A BTMP sheet is treated with 0.3% by weight of Compound B and 2.0% by weight of poly(ethylene glycol), molecular weight 300 (PEO). Again, the treated sheet exhibits an excellent resistance to yellowing as compared to the untreated control sheet.

Example 3**Accelerated Yellowing with High Intensity Lamps**

A BTMP sheet is treated with 0.3% by weight of Compound C and 1.0% by weight of 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole (TINUVIN® 328, Ciba). The treated sheet shows surprisingly excellent resistance to yellowing especially in contrast to the untreated control sheet.

Example 4**Accelerated Yellowing with High Intensity Lamps**

A BTMP sheet is treated with 0.6% by weight of Compound D, 2.0% by weight of poly(ethylene glycol), molecular weight 300 (PEO), and 1.0% by weight of 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole (TINUVIN® 328, Ciba). The treated sheet shows extraordinary resistance to yellowing especially in contrast to the untreated control sheet.

Example 5: Accelerated Yellowing with High Intensity Lamps

A BTMP sheet is treated with 0.3% by weight of Compound A and 1.0% by weight of TINOPAL® SK. Again, the treated sheet exhibits an excellent resistance to yellowing as compared to the untreated control sheet.

Example 6**Accelerated Yellowing with High Intensity Lamps**

A BTMP sheet is treated with 0.3% by weight of Compound B and 1.0% by weight of CIBAFast® W. The treated sheet shows surprisingly excellent resistance to yellowing especially in contrast to the untreated control sheet.

Example 7

A BTMP sheet is treated with 0.33% and with 0.66% by weight of N,N-diethylhydroxylamine (Compound A) and 0.5% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet as seen by inspection of the PC numbers given in the table below. Lower PC numbers indicate less color.

Time in Days	0.5% W 0.66% A <u>PC number</u>	0.5% W 0.33% A <u>PC number</u>	Control <u>PC number</u>
0	0	0	0
0.85	1.18	1.43	2.80
1.84	2.55	2.75	4.71
2.79	3.90	4.24	6.94
3.83	5.46	5.99	8.91
4.75	7.05	7.63	11.03
5.77	8.63	9.23	13.08
6.81	9.92	10.56	14.42
7.75	10.93	11.62	15.57
8.74	11.91	12.53	16.38

Example 8

A BTMP sheet is treated with 0.33% and with 0.66% by weight of tris(N,N-diethyl-hydroxylammonium) citrate (Compound E) and 0.5% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet as seen by inspection of the PC numbers given in the table below. Lower PC numbers indicate less color.

Time in <u>Days</u>	0.5% W 0.66% E <u>PC number</u>	0.5% W 0.33% E <u>PC number</u>	Control <u>PC number</u>
0	0	0	0
0.85	0.94	1.26	2.80
1.84	2.10	2.54	4.71
2.79	3.43	3.94	6.94
3.83	5.31	5.66	8.91
4.75	6.97	7.03	11.03
5.77	8.43	8.71	13.08
6.81	9.98	10.08	14.42
7.75	10.78	10.96	15.57
8.74	11.91	12.18	16.38

Example 9

A BTMP sheet is treated with 1.0% by weight of N,N-bis(2-carboxyethyl)hydroxylamine (Compound F) and 1.0% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

Example 10

A BTMP sheet is treated with 1.0% by weight of N,N-bis(benzylthiomethyl)hydroxylamine (Compound G) and 1.0% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

The following examples 11-20 describe accelerated yellowing tests with high intensity lamps conducted on chemical (Kraft) pulp:

Example 11

A kraft sheet is treated with 1.0% by weight of N,N-diethylhydroxylamine (Compound A) and exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

Example 12

A kraft sheet is treated with 0.3% by weight of Compound B and 2.0% by weight of poly(ethylene glycol), molecular weight 300 (PEO). Again, the treated sheet exhibits an excellent resistance to yellowing as compared to the untreated control sheet.

Example 13

A kraft sheet is treated with 0.3% by weight of Compound C and 1.0% by weight of 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole (TINUVIN® 328, Ciba). The treated sheet shows surprisingly excellent resistance to yellowing especially in contrast to the untreated control sheet.

Example 14

A kraft sheet is treated with 0.6% by weight of Compound D, 2.0% by weight of poly(ethylene glycol), molecular weight 300 (PEO), and 1.0% by weight of 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole (TINUVIN® 328, Ciba). The treated sheet shows extraordinary resistance to yellowing especially in contrast to the untreated control sheet.

Example 15

A kraft sheet is treated with 0.3% by weight of Compound A and 1.0% by weight of TINOPAL® SK. Again, the treated sheet exhibits an excellent resistance to yellowing as compared to the untreated control sheet.

Example 16

A kraft sheet is treated with 0.3% by weight of Compound B and 1.0% by weight of CIBAFast® W. The treated sheet shows surprisingly excellent resistance to yellowing especially in contrast to the untreated control sheet.

Example 17

A kraft sheet is treated with 0.33% and with 0.66% by weight of N,N-diethylhydroxylamine (Compound A) and 0.5% by weight of CIBAFast® W and then exposed to

accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

Example 18

A kraft sheet is treated with 0.33% and with 0.66% by weight of tris(N,N-diethyl-hydroxylammonium) citrate (Compound E) and 0.5% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

Example 19

A kraft sheet is treated with 1.0% by weight of N,N-bis(2-carboxyethyl)hydroxylamine (Compound F) and 1.0% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

Example 20

A kraft sheet is treated with 1.0% by weight of N,N-bis(benzylthiomethyl)hydroxylamine (Compound G) and 1.0% by weight of CIBAFast® W and then exposed to accelerated aging as described above. The treated sheet exhibits a substantial inhibition of yellowing compared to the untreated control sheet.

WHAT IS CLAIMED IS:

1. A composition having reduced loss of brightness and enhanced resistance to yellowing which comprises

(a) a pulp or paper, and

(b) an effective stabilizing amount of an N,N-dialkylhydroxylamine, an ester, amide or thio substituted N,N-dialkylhydroxylamine or N,N-dibenzylhydroxylamine of formula I, II or III






where

R_1 and R_2 are independently alkyl of 1 to 18 carbon atoms, alkyl of 1 to 18 carbon atoms substituted by a hydroxyl group; or benzyl;

T_1 and T_2 are independently alkyl of 1 to 4 carbon atoms, phenyl, 3,5-di-tert-butyl-4-hydroxyphenyl, benzyl or $-CH_2COOH$;

E_1 and E_2 are independently $-OE_3$, $-NHE_3$ or $-NE_3E_4$ where E_3 and E_4 are independently hydrogen, alkyl of 1 to 4 carbon atoms or said alkyl substituted by one hydroxyl group; or

of an acid salt of formula IA, IIA or IIIA



where

R_1 , R_2 , T_1 , T_2 , E_1 and E_2 are as defined above,

X is an inorganic or organic anion, and

the total charge of cations h is equal to the total charge of anions j.

2. A composition according to claim 1 wherein component (a) is a pulp or paper which still contains lignin.

3. A composition according to claim 1 wherein component (a) is a chemimechanical or thermomechanical or kraft pulp or paper.

4. A composition according to claim 1 where in the formula IA, IIA or IIIA, X is phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride, bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid, hydroxyethylethylene-diaminetriacetic acid, ethylenediaminetetraacetic acid or of diethylenetriaminepentaacetic acid, a diethylenediaminetetraacetic acid or of diethylenetriaminepentaacetic acid, an alkylsulfonate or an arylsulfonate.

5. A composition according to claim 1 wherein component b is N,N-dimethylhydroxylamine, N,N-diethylhydroxylamine, N,N-bis(2-hydroxypropyl)hydroxylamine, N,N-bis(3-hydroxypropyl)hydroxylamine, N,N-dioctadecylhydroxylamine, the N,N-dialkylhydroxylamine product made by the direct oxidation of N,N-di(hydrogenated tallow)amine, N,N-dibenzylhydroxylamine, N,N-bis(2-carboxyethyl)hydroxylamine or N,N-bis(benzylthiomethyl)hydroxylamine, or a corresponding acid salt.

6. A composition according to claim 1 which additionally includes an effective stabilizing amount of at least one coadditive selected from the group consisting of the UV absorbers, the polymeric inhibitors, the sulfur containing inhibitors, the phosphorus containing compounds, the nitrones, the benzofuran-2-ones, fluorescent whitening agents, hindered amine hydroxylamines and salts thereof, hindered amine nitroxides and salts thereof, hindered amines and salts thereof, and metal chelating agents.

7. A composition according to claim 6 wherein the additional stabilizer is
a UV absorber selected from group consisting of the benzotriazoles, the s-triazines, the benzophenones, the α -cyanoacrylates, the oxanilides, the benzoxazinones, the benzoates and the α -alkyl cinnamates;
a polymeric inhibitor selected from poly(ethylene glycol), poly(propylene glycol), poly(butylene glycol) or poly(vinyl pyrrolidone);
a sulfur containing inhibitor selected from the group consisting of polyethylene glycol dithiolacetate, polypropylene glycol dithiolacetate, polybutylene glycol dithioacetate, 1-thioglycerol, 2-mercaptoethyl ether, 2,2'-thiodiethanol, 2,2'-dithiodiethanol, 2,2'-oxydiethanethiol, ethylene glycol bithioglycolate, 3-mercapto-1,2-propanediol, 2-(2-methoxyethoxy)-ethanethiol, glycol dimercaptoacetate, 3,3'-dithiopropionic acid, polyethylene glycol dithiol, polypropylene glycol dithiol, polybutylene glycol dithiol and ethylene glycol bis(mercaptoacetate); and/or
a phosphorus containing compound selected from the group consisting of tris(2,4-di-tert-butylphenyl) phosphite, 2,2',2"-nitrido[triethyl-tris(3,3',5,5'-tetra-tert-butyl-1,1'-biphenyl-2,2'-diyl) phosphite], tris(2,4-di-tert-butyl-6-ethylphenyl) phosphite, sodium hydroxymethyl phosphinate, tetrakis(2,4-di-butylphenyl) 4,4'-biphenylenediphosphonite, tris(nonylphenyl) phosphite, bis(2,4-di-tert-butylphenyl) pentaerythrityl diphosphite, 2,2'-ethylidenebis(2,4-di-tert-butylphenyl) fluorophosphite and 2-butyl-2-ethylpropan-1,3-diyl-2,4,6-tri-tert-butylphenyl phosphite.

8. A composition according to claim 6 wherein the additional stabilizer is a mixture containing two of the following components:
a UV absorber and polymeric inhibitor; a UV absorber and a sulfur containing compound; a UV absorber and a phosphorus containing compound; a UV absorber and a metal chelating agent; a polymeric inhibitor and a sulfur containing compound; a polymeric inhibitor and a phosphorus containing compound; a sulfur containing compound and a phosphorus containing compound; a UV absorber and a hindered amine;

9. A composition according to claim 1 wherein the effective stabilizing amount of the hydroxylamine or hydroxylamine salt of component b is 0.001 to 5% by weight based on the pulp or paper.

10. A composition according to claim 7 wherein the effective stabilizing amount of a coadditive is 0.001 to 5% by weight based on the pulp or paper.

11. A process for preventing the loss of brightness and for enhancing resistance to yellowing of pulp or paper which comprises

treating said pulp or paper with an effective stabilizing amount of a hydroxylamine compound of formula I, II or III or hydroxylamine salt of formula IA, IIA or IIIA according to claim 1.

12. Use of a hydroxylamine compound of formula I, II or III or hydroxylamine salt of formula IA, IIA or IIIA according to claim 1 for stabilizing pulp or paper against loss of brightness and yellowing.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/07594

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D21C9/00 D21H21/14 D21H17/07

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21C D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 717 143 A (LIGNOZYM GMBH) 19 June 1996 (1996-06-19) page 5, line 24 - line 59 ---	1-3,5
A	DATABASE WPI Section Ch, Week 198412 Derwent Publications Ltd., London, GB; Class A92, AN 1984-071908 XP002128731 & JP 59 026464 A (UNITIKA LTD), 10 February 1984 (1984-02-10) abstract ---	1-4,9-12
A	US 3 832 277 A (SMITH F ET AL) 27 August 1974 (1974-08-27) the whole document ---	1-12
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

2 February 2000

Date of mailing of the international search report

15/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bernardo Noriega, F

INTERNATIONAL SEARCH REPORT

Inter national Application No

PCT/EP 99/07594

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 4 612 393 A (RAVICHANDRAN RAMANATHAN ET AL) 16 September 1986 (1986-09-16) cited in the application the whole document</p> <p>-----</p>	1-12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/07594

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0717143 A	19-06-1996	AT 171228 T	15-10-1998
		AU 688660 B	12-03-1998
		AU 4535096 A	03-07-1996
		BR 9506801 A	30-06-1998
		CA 2164394 A	17-06-1996
		CN 1142255 A	05-02-1997
		CZ 9602438 A	15-01-1997
		DE 59503612 D	22-10-1998
		WO 9618770 A	20-06-1996
		EP 0745154 A	04-12-1996
		ES 2122722 T	16-12-1998
		FI 963210 A	16-08-1996
		HU 76126 A, B	30-06-1997
		JP 9503257 T	31-03-1997
		NO 963410 A	15-10-1996
		NZ 300571 A	26-01-1998
		PL 315913 A	09-12-1996
		SK 104096 A	05-02-1997
JP 59026464 A	10-02-1984	NONE	
US 3832277 A	27-08-1974	NONE	
US 4612393 A	16-09-1986	CA 1258470 A	15-08-1989
		EP 0206979 A	30-12-1986
		JP 61254557 A	12-11-1986

This Page Blank (uspto)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

This Page Blank (uspto)